






Kennzeichnung	Klasse nach SAE J-429	Prüfkraft		Streckfestigkeit		Zugfestigkeit	
		psi	N/mm ²	psi	N/mm ²	psi	N/mm ²
	Grade 2	33.000	227,5 ₃	36.000	248,2 ₁	60.000	413,69
	Grade 5	74.000	510,2 ₁	81.000	558,4 ₈	105.000	723,95
	Grade 5.2	85.000	586,0 ₅	92.000	634,3 ₂	120.000	827,37
	Grade 7	105.000	723,9 ₅	115.000	792,9 ₀	133.000	917,00
	Grade 8	120.000	827,3 ₇	130.000	896,3 ₂	150.000	1034,2 ₀